





















8,00 mm / COLOURED BODY PORCELAIN STONEWARE

| | Reference standard E.N. 14411 . Appendix G. Group Bla. GL | Test method | Reference value | Declared value |
|---|---|-------------|-----------------|--------------------------|
|  | Surface abrasion | ASTM-C1027 | - | III (Nutmeg, Nero) |
|  | Surface abrasion | ASTM-C1027 | - | IV |
|  | Water absorption | ASTM-C373 | - | ≤ 0.5% |
|  | Chemical resistance | ASTM-650 | - | CLASS A |
|  | Dynamic coefficient of friction | ANSI-137-1 | - | ≥ 0.42* MATTE |
|  | Dynamic coefficient of friction | ANSI-137-1 | - | ≥ 0.35* SEMIPOLISHED |
|  | Stain Resistance | ASTM-C1378 | - | CLASS A |
|  | Breaking strength | ASTM-C648 | - | > 400 (9mm), > 300 (8mm) |
|  | Resistance to freeze | ASTM-C1026 | - | RESISTANT |
|  | Scratch hardness | MOHS | - | ≥ 7 |

10,00 mm / COLOURED BODY PORCELAIN STONEWARE

| | Reference standard E.N. 14411 . Appendix G. Group Bla. GL | Test method | Reference value | Declared value |
|---|---|-------------|-----------------|--------------------|
|  | Surface abrasion | ASTM-C1027 | - | III (Nutmeg, Nero) |

| | | | | |
|---|---------------------------------|------------|---|--------------------------|
|  | Surface abrasion | ASTM-C1027 | - | IV |
|  | Water absorption | ASTM-C373 | - | ≤ 0.5% |
|  | Chemical resistance | ASTM-650 | - | CLASS A |
|  | Dynamic coefficient of friction | ANSI-137-1 | - | ≥ 0.42* MATTE |
|  | Dynamic coefficient of friction | ANSI-137-1 | - | ≥ 0.35* SEMPOLISHED |
|  | Stain Resistance | ASTM-C1378 | - | CLASS A |
|  | Breaking strength | ASTM-C648 | - | > 400 (9mm), > 300 (8mm) |
|  | Resistance to freeze | ASTM-C1026 | - | RESISTANT |
|  | Scratch hardness | MOHS | - | ≥ 7 |