










SPECIFICATION REFERENCE E.N. 14411 · APPENDIX G · GROUP B1A · GL	TEST METHOD	REFERENCE VALUE		DECLARED VALUE
	<i>Dynamic coefficient of friction</i>	<i>ANSI-137-1</i>	-	$\geq 0.50$ GRIP
	<i>Dynamic coefficient of friction</i>	<i>ANSI-137-1</i>	-	$\geq 0.42$ NATURAL
	<i>Chemical resistance</i>	<i>ASTM-650</i>	-	NOT AFFECTED
	<i>Resistance to freeze</i>	<i>ASTM-C1026</i>	-	RESISTANT
	<i>Surface abrasion</i>	<i>ASTM-C1027</i>	-	IV
	<i>Stain resistance</i>	<i>ASTM-C1378</i>	-	NOT AFFECTED
	<i>Water absorption</i>	<i>ASTM-C373</i>	-	$\leq 0.5\%$
	<i>Breaking strength</i>	<i>ASTM-C648</i>	-	$\geq 400$
	<i>Scratch hardness</i>	<i>MOHS</i>	-	$\geq 7$