



TECHNICAL FEATURES

TECHNICAL PORCELAIN

DIN 51130 DIN 51097 LINE-EN/12633 ASTM C 1028	ISO 10545-14	ISO 10545-13	ISO 10545-12	ISO 10545-9	ISO 10545-8	ISO 10545-6	ISO 10545-4	ISO 10545-3	ISO 10545-2	STANDARD NORMES
According to models	Minimum class 3	Test method available	Test method available	Test method available	Test method available	Máx.175 mm ²	> 35 N/mm ² > 1800 N	< 0,5%		VALUE REQUIRED BY EN 14411 STANDARD
	Conforms to Standard	Conforms to Standard	Resists	Resists	< 7,0 x 10 ⁻⁴ °C ⁻¹	110-130 mm ²	35-45 N/mm ² 1800-2500 N	0,1%	Conforms to Standard	AVERAGE VALUE

GROUP BLA WATER ABSORPTION <0.5% / GRUPO BLA ABSORCIÓN DE AGUA <0.5%

- Slip Resistance
- Resistance to stains
- Chemical resistance
Acids and bases
Cleaning products and
pool reactive agents
- Frost resistance
- Thermal shock resistance
- Linear thermal expansion
- Resistance to deep abrasion (mm³)
- Modulus of rupture
- Water absorption
- Dimensional Features

USES AND APPLICATIONS / USOS Y APLICACIONES

- Residential
- Offices
- Hotels
- Buildings
- Schools
- Hospitals
- Restaurants
- Department stores
- Sport areas
- C-Grip



▼ Geo - 200 Naturale



▼ Geo - 201 Naturale



▼ Geo - 202 Naturale



▼ Geo - 203 Naturale

