







	Regulation	Required standards	Value	
 Dimensioni/Sizes/Dimensions/Abmessungen/Afmetingen/Dimensiones	UNI EN ISO 10545/2	Non rettificato Not rectified → Lunghezza e larghezza/Length and width/Longueur et largeur/Länge und Breite/Lengte en breedte/Longitud y anchura → Spessore/Thickness/Épaisseur/Stärke/Dikte/Grosor → Rettilineità spigoli/Linearity/Rectitude des arêtes/Kantengeradheit/Rechtheid kanten/Rectitud de los lados → **Ortogonalità/Wedging/Orthogonalité/Rechtwinkligheid/Heekheid hoeken/Ortogonalidad → Planarità/Warpage/Planéité/Ebenfächigkeit/Vekheid/Planitud	±0.6 % max 2mm ±5 % max 0.5mm ±0.5 % max 1.5mm ±0.5 % max 2mm ±0.5 % max 2mm ±0.3 % max 1mm ±5 % max 0.5mm ±0.3 % max 0.8mm ±0.3 % max 1.5mm ±0.4 % max 1.8mm	Conforme Compliant
	UNI EN ISO 10545/3	≤ 0.5 %	0.2%	
	UNI EN ISO 10545/4	≥ 35 N/mm ²	Conforme Compliant	
		S ≥ 1300 N (thickness ≥ 7.5 mm)	Conforme Compliant	
	UNI EN ISO 10545/6	≤ 175 mm ³	Conforme Compliant	
 Coefficiente di dilatazione termica lineare/Coefficient of thermal linear expansion/Coefficient de dilatation thermique linear/Lineare Wärmeausdehnungskoeffizient/Lineaire thermische uitzetting /Coeficiente de dilatación termica linear	UNI EN ISO 10545/8	Metodo di prova disponibile/Tests method available/Methode d'essai disponible/Verfügbares/Prüfverfahren/Testmethode beschikbaar/Método de prueba disponible	≤ 7 · MK ¹	
 Resistenza al gelo/Frost resistance/Résistance au gel/Frostbeständigkeit/Vorstbestandheid/Resistencia a la helada	UNI EN ISO 10545/12	Resistenti/Resistant/Resistants/Widerstandsfähig/Weerbaarstig/Resistentes	Conforme Compliant	
 Resistenza all'attacco chimico/Chemical resistance/Resistance à l'attaque chimique/Beständigkeit gegen Chemikalien/Chemische bestandheid/Resistencia al ataque químico	UNI EN ISO 10545/13	Metodo di prova disponibile/Tests method available/Methode d'essai disponible/Verfügbares/Prüfverfahren/Testmethode beschikbaar/Método de prueba disponible	ULA - UHA	
 Resistenza alle macchie/Stain resistance/Insensibilité aux taches/Beständigkeit gegen Fleckenbildner/Substanzen/Weerstand tegen vlekken/Resistencia a las manchas	UNI EN ISO 10545/14	UGL Dichiarare un valore / UGL Declare a value	Classe 5 Class 5	
 Indicazione di resistenza allo scivolamento/Assessment of slip resistance/Indication de la résistance au glissement/Bestimmung der Trittsicherheit/Indicatie voor de slipvastheid/Indicación de resistencia al deslizamiento	DIN 51130	Dichiarare un valore (R) / Declare a value (R)	Matt: R10	
	DIN 51097	Dichiarare un valore (A+B+C) / Declare a value (A+B+C)		
	BS 7976-2:2002 (EN) 13, 16, 165, Annex C) Pendulum Friction Test	Dichiarare un valore / Declare a value		
 Coefficiente di attrito dinamico/Measurement of dynamic coefficient of friction/Mesure du coefficient de frottement dynamique/Messung des dynamischen Reibungskoeffizienten/Meting van de dynamische wrijvingscoëfficiënt/Coeficiente de rozamiento dinámico	B.C.R.A. Rep. CEC/81	Asciutto > 0.40 / Bagnato > 0.40	Matt: Asciutto > 0.40 / Bagnato > 0.40	
	ANSI A137.1-2012 (BOT3000)	> 0.42 Wet	Matt: > 0.42 Wet Soft: > 0.42 Wet	

**Per piastrelle rettangolari, che abbiano il lato maggiore L ≥ 60 cm, e rapporto tra i lati ≥ 3, la misurazione della ortogonalità deve venire condotta solo sui lati corto.
For oblong tiles with L ≥ 60 cm and ratio length/width L/W ≥ 3, measurement of rectangularity only on short edges

I valori indicati nella tabella si riferiscono a superfici naturali (non Lappato e Soft)/The values in the table refer to natural (not Lappato - honed - and Soft) surfaces /Les valeurs du tableau se rapportent à des surfaces naturelle (non Lappato - adoucis - et Soft)/Die in der Tabelle angeführten Werte beziehen sich auf naturbelassene (nicht Lappato - geispte - und Soft) Oberflächen/De waarden in de tabel hebben betrekking op natuurlijke oppervlakken (niet Lappato - zijgeglans - en Soft)/Los valores indicados en la tabla se refieren a las superficies naturales (no Lappato - semipulido - y Soft)

MATT and SOFT finishes are recommended for interior floors, walls, and exterior walls in both residential and commercial applications. It is not recommended for exterior horizontal surfaces or exterior paving, and it is not recommended for ramps application. SOFT finish is not recommended for interior floors in entrance areas if joined to outdoor in commercial applications. LAPPATO is recommended for interior walls, and exterior walls in both residential and commercial applications. LAPPATO finish is not recommended for floors.